

**PRODUCT TECHNICAL
DATA SHEET
No. 43 – 5 – G
March 2022**

JSC “Mida LT”

Gamyklos 19, Gargzdai LT96121, Lithuania

Characteristics of the product: MIDA LIGHT G– is bitumen sheeting membrane for application with cold adhesive or hot bitumen mastic, can also be fastened mechanically.

Produced in accordance with the requirements of EN 13707:2004+A2:2009. Carrier- glass fibre.

The product is surfaced with grit on the upper side and with sand on the underside.

To be used as underlayment.

Do not use as single or upper layer and for roof gardens.

MIDA LIGHT G Technical data

| Characteristics | Test method / (classification) | Units | Expression of result ^a | Value or statement | Declared tolerances |
|--|--------------------------------|-------------------|-----------------------------------|------------------------|---------------------|
| Visible defects | EN 1850-1 | – | Visible defects | - | |
| Length | EN 1848-1 | m | MLV | 10,0 | |
| Width | EN 1848-1 | m | MLV | 1,0 | |
| Straightness | EN 1848-1 | mm | Pass | 10 m ≤ 20 mm | |
| Mass per unit area | EN 1849-1 | kg/m ² | MDV | 1,8 | ± 0,2 |
| Thickness | EN 1849-1 | mm | MDV | 1,2 | ± 0,1 |
| Watertightness | EN 1928, Method B | kPa | Pass | Pass | |
| Watertightness after stretching at low temperature | EN 13897 | % | MLV | - | |
| External fire performance | ENV 1187 | – | EN 13501-5 | F _{ROOF} (t1) | |
| Reaction to fire | EN 13501-1+A1 | – | EN 13501-1+A1 | E | |
| Peel resistance of joint | EN 12316-1 | N/50 mm | MDV | - | |
| Joint strength (Shear resistance) | EN 12317-1 | N/50 mm | MDV | - | |
| Tensile properties: maximum tensile force | EN 12311-1 | N/50 mm | MDV | 400 / 300 | - 150 |
| Tensile properties: elongation | EN 12311-1 | % | MDV | 4 | - 2 |
| Resistance to impact | EN 12691 | mm | MLV | - | |
| Resistance to static loading | EN 12730 | Kg | MLV | - | |
| Resistance to tearing (nail shank) | EN 12310-1 | N | MDV | 60 | - 30 |
| Resistance to root penetration | EN 13948 | – | Pass | – | |
| Dimensional stability | EN 1107-1 | % | MLV | - | |
| Form stability under cyclic temperature change | EN 1108 | mm | MLV | - | |
| Flexibility at low temperature | EN 1109 | °C | MLV | 0 | |
| Flow resistance at elevated temperature | EN 1110 | °C | MLV | 90 | |
| Artificial ageing by long term exposure to elevated temperature | EN 1296 | See EN 1109 | MDV | - | |
| Artificial ageing by long term exposure to combination of UV radiation, elevated temperature and water | EN 1297 | See EN 1850-1 | Pass | – | |
| Adhesion of granules | EN 12039 | % | MDV | - | |
| Water vapour transmission properties | EN 1931 | – | μ = MDV or 20 000 | 20 000 | |

^a - MLV: manufacturer limiting value according to 3.9 EN 13707; MDV: manufacturer declared value according to 3.10 EN 13707.

– not relevant

NPD- no performance determined

References of manufacturer:

The rolls should be stored and transported in vertical position and protected against moisture, heat and mechanical damage.

Storage temperature 0 - +40°C

In the cold season the rolls should be kept in a warm, dry place at the temperature more than +10°C for not less than 12 hours before use.